



INVESTOR IN PEOPLE

The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

The undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Controller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

I also certify that the attached copy of the request for grant of a Patent (Form 1/77) bears an endorsement, effected by this office, following a request by the applicant and agreed to by the Controller-General.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.


In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Dated

*P. Mahoney*  
7 April 2004



15DEC03 E859340-1 010128  
P01/7700 0.00-0328948.5 ACCOUNT CHA

# Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road  
Newport  
South Wales  
NP10 8QQ

1. Your reference

9292

2. Patent application number

(The Patent Office will fill this part in)

13 DEC 2003

0328948.5

3. Full name, address and postcode of the or of each applicant (underline all surnames)

MILLIKEN EUROPE NV  
18 HAM  
9000 GENT

04374443002

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

BELGIUM

4. Title of the invention

COMPOSITE ARTICLE AND ITS MANUFACTURE

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

STEPHEN BRISTOW  
MILLIKEN INDUSTRIALS LIMITED  
BEECH HILL PLANT  
GIDLOW LANE  
WIGAN  
WNG 8RN

Hoffmann Eihe  
Sardinia House  
Sardinia Street  
52 Lincoln's Inn Fields  
LONDON  
WC2A 3LZ

Patents ADP number (if you know it)

06625024001

0715646601 M8 2/4/64

6. Priority: Complete this section if you are declaring priority from one or more earlier patent applications, filed in the last 12 months.

Country

Priority application number  
(if you know it)

Date of filing  
(day / month / year)

N/A

7. Divisionals, etc: Complete this section only if this application is a divisional application or resulted from an entitlement dispute (see note f)

Number of earlier UK application

Date of filing  
(day / month / year)

N/A

8. Is a Patents Form 7/77 (Statement of inventorship and of right to grant of a patent) required in support of this request?

Answer YES if:

- a) any applicant named in part 3 is not an inventor, or
- b) there is an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body:

Otherwise answer NO (See note d)

YES

# Patents Form 1/77

9. ( ) accompanying documents: A patent application must include a description of the invention. Not counting duplicates, please enter the number of pages of each item accompanying this form:

Continuation sheets of this form	0
Description	9
Claim(s)	2 DL
Abstract	0
Drawing(s)	1 + 1

10. If you are also filing any of the following, state how many against each item.

Priority documents	0
Translations of priority documents	0
Statement of inventorship and right to grant of a patent (Patents Form 7/77)	0
Request for a preliminary examination and search (Patents Form 9/77)	✓
Request for a substantive examination (Patents Form 10/77)	0
Any other documents (please specify)	FEE SHEET ✓

11. I/We request the grant of a patent on the basis of this application.

Signature(s)

S. R. Bristow

Date 12 December 2003

12. Name, daytime telephone number and e-mail address, if any, of person to contact in the United Kingdom

STEPHEN BRISTOW  
01942 612959 Stephen.bristow@milliken.com

## Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

## Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered YES in part 8, a Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- Part 7 should only be completed when a divisional application is being made under section 15(4), or when an application is being made under section 8(3), 12(6) or 37(4) following an entitlement dispute. By completing part 7 you are requesting that this application takes the same filing date as an earlier UK application. If you want the new application to have the same priority date(s) as the earlier UK application, you should also complete part 6 with the priority details.

## COMPOSITE ARTICLE AND ITS MANUFACTURE

Technical Field

5 This invention relates to a composite article comprising a silicone rubber matrix reinforced with polyaramid textile that is bonded to the silicone rubber matrix. The invention also relates to a method to manufacture the article and in particular to a method to obtain a strong bond between the polyaramid textile and the silicone rubber.

Background to the Invention

10 WO 03/066943 describes the production of a coated polyaramid and the use of this coated polyaramid to produce a reinforced article. A range of matrix materials is given; silicones are among the listed materials. Yarns of poly-p-phenylene terephthalamide (p aramid) are first coated with a curable epoxy compound before application of a second coat of resorcinol-formaldehyde-latex (RFL) and then bonding the double coated polyaramid to a rubber or a rubber like material. The epoxy compound preferably comprises di and/or triglycidyl ether of glycerol or  
15 the polyglycidyl ether of polyglycerol. It is stated that the advantage of the invention is that the epoxy pre-coated polyaramid has a good RFL pickup. The use of such a bonding system for silicone rubber has been found to be unsatisfactory due to the unsuitability of RFL as a bonding agent for silicone rubbers. It is desirable to develop a suitable bonding system for silicone rubber because for many high temperature applications, such as turbo hoses for cars, other rubber types  
20 are less suitable. Furthermore many reinforcement cords are also unsuited for such high temperature yet low modulus applications. It is therefore an objective to make a strong bond between polyaramid and silicone rubber.

JP4057821 describes a polysulphide modified epoxy resin prepreg composition for polyaramid fibre. The use of this coated polyaramid as a reinforcement for silicone rubber is not disclosed.

25 JP9124801 describes the coating of polyaramid with polyamide resin in order to improve its bonding to a matrix of epoxy resin.

Organosilanes are well known as bonding agents. Trialkoxyorganosilanes have been used to enhance adhesion of organic polymers to inorganic substrates such as glass and metals. Trialkoxyorganosilanes are hypothesized to promote adhesion through a combination of a coupling  
30 mechanism and the formation of interpenetrating networks via hydrolysis of the alkoxy groups to form silanols which then condense to form silsesquioxane networks. Trimethoxysilanes are the preferred trialkoxyorganosilanes for this purpose.

3-methacryloxypropyl-trimethoxysilane is offered by many silane coupling agent manufacturers as suitable for coupling organic materials, such as butyl polyester, polyether, polyolefin and inorganic


materials, such as glass fiber. In US 6,046,262 there is described a dip system comprising a mixture of an aminosilane with another organosilane. In comparative example 5 a 100% polyester fabric sample was dipped into an aqueous dispersion of the organosilane methacryloxypropyltrimethoxysilane and dried. The fabric was then impregnated with resorcinol formaldehyde vinylpyridine latex (RFL) and bonded to SBR. The bond peel strength was shown to be inferior to a sample coated using a dip comprising methacryloxypropyltrimethoxysilane and an aminosilane.

In US 6 096 156 low-pressure plasma treatment of polyaramids to improve their bonding to coatings and rubber is described. A polyaramid cord (Twaron®) is subjected to low pressure plasma treatment including a first plasma stage in which the cord is cleaned by exposure to a plasma containing O<sub>2</sub> and CF<sub>4</sub> and a second plasma stage in which the cord is plasma coated by exposure to a plasma containing a vinyl compound; such as: acrylic acid, ethylene, butadiene, vinyl pyridine. After this plasma treatment the cord may optionally be further activated by coating with an epoxy compound before it is coated with the usual RFL and bonded to rubber. No mention is made of silicone rubber. It is suggested that the plasma treated polyaramid may have a coating of polysiloxane tackifier applied before bonding it to rubber. This tackifier would be applied over the RFL.

Dow Corning Q-1-6106 adhesion promoter is described in the Material safety data sheet from Dow as being 10 to 30% glycidoxypopyl trimethoxysilane. Dow's product information sheet for Q-1-6106 states that this adhesion promoter will "provide coupling of most reinforcing agents such as glass or Kevlar® to most polar organic polymers and engineering plastics". Rubbers are not listed among these.

#### Disclosure of Invention

According to the present invention there is provided a composite article comprising a polysiloxane or silicone rubber matrix reinforced with polyaramid textile characterized in that the polyaramid textile is bonded to the silicone rubber by means of a bonding composition comprising an acryloxy organosilane of formula (I):




In formula (I) R<sup>1</sup> is a moiety selected from methyl, ethyl, combinations thereof and methoxyethyl,

R<sup>2</sup> is a moiety selected from methoxy, ethoxy, methyl, ethyl, and methoxyethoxy.

R<sup>4</sup> is selected from C<sub>2</sub>-C<sub>8</sub> alkylene, branched or unbranched.


$R^5$  is a moiety selected from hydrogen and methyl and is preferably methyl.

Preferred acryloxy organosilanes have formula (II)



5 Where  $R^6$  is  $C_2$ - $C_4$  alkylene and  $R^5$  is as defined in formula (I).

The most preferred acryloxy organosilane is 3-methacryloxypropyl trimethoxysilane, which has the formula (III):




10 Preferably to obtain the best adhesion the polyaramid is precoated or activated with an epoxy compound. The preferred epoxy compounds are selected from the group comprising di and/or tri glycidyl ethers of glycerol; a suitable diglycidyl ether is GE100 glycidyl ether 100 from Raschig Chemicals. An alternative epoxy compound that may be used is a polyglycidyl ether of polyglycerol; a suitable polyglycerol glycidyl ether is GE500 from Raschig Chemicals.

15 Any of the well known polyaramids may be utilized in the present invention, a p-phenylene polyaramid such as that known under the trade name Twaron® or Kevlar® or a m-phenylene polyaramid such as that known under the trade name Nomex®, or even a mixed meta and para polyaramid or copolymers which comprise also naphthalenic units and are known under the trade name Technora®. Generally the more one moves away from the relatively inextensible purely p-phenylene forms the more suited the yarns produced therefrom are to the reinforcement of rubber.

20 Extensibility is good for the bonding of the polyaramid to the rubber as the closer matching of modulus gives less stress on the bond when the composite is compressed or stretched.


Throughout this patent specification the expression polyaramid textile includes all ways to use polyaramid yarn, for example the polyaramid yarn may be in the form of a cord made from twisted together yarns, or it may be in the form of a fabric, which can be processed as a web. A preferred fabric construction has the polyaramid cord knitted as a warp yarn and / or as a weft yarn in a weft insertion warp knit process. The polyaramid may be provided as an inlay warp yarn or as a weft inserted yarn or both. Other textile constructions are also possible.

Advantageously the organosilane bonding composition further comprises an epoxy organosilane. The combination of different organosilanes in this way allows one of the silanes to be optimized for adhesion to the silicone and the other to be optimized for adhesion to the polyaramid or epoxy coated polyaramid. A preferred epoxy silane is shown in formula (IV):




Wherein  $\text{R}^1$ ,  $\text{R}^2$  and  $\text{R}^4$  have the same meanings as defined for formula (I) and  $\text{R}^7$  is selected from the group comprising gamma glycidoxy and 2(3,4 epoxycyclohexyl). Preferably  $\text{R}^2$  is  $\text{OR}^1$  and most preferably  $\text{R}^1$  is methyl. Preferably  $\text{R}^4$  is propyl and most preferably the epoxy organosilane is gamma-glycidoxypropyl trimethoxysilane.

The composition may also include a vinyl organosilane of formula (V).



Wherein  $\text{R}^3$  is selected from the group comprising methoxy, ethoxy and chlorine moieties. Preferably the vinyl organosilane is vinyl trimethoxysilane.

In the case that the process used to coat the polyaramid includes plasma activation of the cord the organosilane composition may further comprise an amino organosilane. The amino organosilane may have the formula (VI):



Wherein  $\text{R}^1$ ,  $\text{R}^2$  and  $\text{R}^4$  have the same meanings as defined for formula (I) and  $\text{R}^6$  is selected from the group comprising hydrogen, phenyl and ethylamino. Preferably the amino organosilane is N-phenyl gamma aminopropyl trimethoxysilane.

5 Also according to the invention there is a process for manufacturing an polyaramid reinforced silicone rubber article comprising the steps of:

a) Selecting a polyaramid textile,

b) Optionally activating the polyaramid textile with an epoxy compound, and/or optionally activating the polyaramid textile with plasma,

10 c) Dipping the polyaramid textile into an organosilane dip comprising acryloxy organosilane,

d) Bonding the dipped polyaramid textile to silicone rubber.

Preferably the organosilane dip further comprises an epoxy organosilane. For environmental and health reasons it is preferred that the organosilane dip is an aqueous dip. By aqueous we mean a solution or dispersion of organosilane, which comprises a major part of water. As a co-solvent  
15 there may also be a minor part of an organic solvent, such as methanol or IPA, or other alcohols.

It is advantageous if the epoxy activation and the organosilane dipping steps are carried out separately and with drying after each step. The drying is preferably done at elevated temperature in an oven.

To further improve the cover and / or the bond strength of the organosilane or other coating  
20 material applied from the dips it is advantageous to activate the polyaramid with plasma before dipping. Preferably the plasma treatment is applied to a dry polyaramid and most preferably it is applied to a polyaramid that has already been activated with epoxy compound. It is most advantageous if the plasma treatment is done by means of use of air plasma. In the case where the epoxy compound has been dried before a dip containing a mixture of acryloxy organosilane  
25 and amino functional organosilane as described, for example, in US 6,046,262, an air plasma comprising an aerosol of glycerol in a nitrogen carrier, perhaps also with an alcohol diluent such as IPA is preferred. An atmospheric air plasma treatment is preferred for use before organosilane dips that do not contain an amino functional organosilane. Preferred epoxy compounds are as



described above, the epoxy compound needs to be dispersed in a suitable medium for dipping as described in WO 03/066943.

The epoxy functional organosilane may be used in combination with a vinyl organosilane.

It is preferred that the polyaramid textile is in the form of a cord or a fabric including such a cord.

5 The invention will now be further described with reference to the following non-limiting examples and with reference to the figures of which

Figure 1 is a schematic representation of a polyaramid cord treatment process; and

Figure 2 is a cord reinforced rubber article before pressing and vulcanization.

10 Figure 1 shows a polyaramid yarn or cord 1 being drawn from a feed roll 2. In this example the yarn is a 1680 decitex p-phenylene polyaramid yarn. The yarn is optionally activated before it is coated with acryloxy organosilane. Activation can be by means of epoxy and/or plasma. In the case where epoxy activation is used one means to achieve that activation is to pass the yarn over tensioning and feed roller 3 and into a dip bath 4. When this optional dip bath 4 is used it contains an epoxy dip 5, which has been prepared as described in example 1 of WO 03/066943. If the yarn  
15 or cord is dipped into the epoxy compound dip 5 it is then dried in a pair of air ovens 6a, 6b at a temperature of about 150 °C to activate the polyaramid. The tension of the yarn 1 through the epoxy compound dip 5 and the oven 6 is about 25 mN/tex.

Alternative methods to activate the yarn or cord with the epoxy compound may be used. For example it can be applied during the spin finishing or drawing of the yarn, it may even be applied  
20 during an aerosol plasma treatment. It is preferred to twist the yarn before it enters dip 5. After coating with epoxy and drying, the yarn is preferably twisted to form a cord if the yarn 1 is not already a cord. For our examples we used a 2 ply cord of 3360 decitex. Samples of dried polyaramid cord with or without epoxy activation were optionally subjected to a plasma activation treatment. In a first optional plasma activation treatment, the cord or yarn was exposed to air  
25 plasma in plasma apparatus 7. In an alternative optional plasma activation treatment the cord was activated by exposure in plasma apparatus 7 to an air plasma that contained an aerosol of glycol or glycerol in a nitrogen carrier, this latter option being intended to promote maximum activation of the surface of the cord in the case where an amino functional organosilane is used in admixture with the acryloxyorganosilane in the subsequent silane dip. The plasma treatment 7 is shown as  
30 being after the epoxy activation but it could alternatively or additionally be carried out before the epoxy activation or in place of the epoxy activation.

The cord 12a is passed to a dip bath 8 to be coated using an aqueous organosilane dip 9 having one of the compositions A, B C or D as detailed in table 1. Table 2 indicates which cords were subjected to plasma activation before being passed into organosilane dip 9. The dip-coated cord  
35 12b was removed from dip bath 8 and then air-dried in air ovens 10 and 11 before the coated cord

12b was wound onto storage roll 13. The dip coating conditions in all cases were to pull the cord through the dip 9 and the air-drying ovens 10 and 11 under a tenacity of about 25 mN per tex. The temperature of the ovens 10 and 11 was maintained in the range 170 to 260 °C.

- 5 The coated cord 12b was subsequently bonded to a peroxide cured silicone rubber obtained from Wacker under the name Elastosil R760/70-MH-C1 H3 and vulcanized, as will be described in further detail with reference to figure 2.

Table 1 – Organosilane Dip

	Acryloxy silane	Epoxy silane	Vinyl silane	Amino silane
Dip A	gamma-methacryloxypropyl trimethoxysilane	-	-	-
Dip B	gamma-methacryloxypropyl trimethoxysilane	gamma-glycidoxypopyl trimethoxysilane	-	-
Dip C	gamma-methacryloxypropyl trimethoxysilane	gamma-glycidoxypopyl trimethoxysilane	vinyl trimethoxysilane	-
Dip D	gamma-methacryloxypropyl trimethoxysilane	-	-	N-phenyl gamma aminopropyl trimethoxysilane

- 10 The total weight percentage of organosilane in the dip is not critical. However, we found that generally the amount of the organosilanes used should be approximately equal and total to a weigh percentage in the range 1-5%. The exception to this is the amino organosilane which should only be used at a comparatively low level of below 0.5%. The organosilanes used were as follows:

- 15 The gamma-methacryloxypropyl trimethoxysilane used was Silquest A174 for dip A, Silquest A174NT for dips B and D and Z6040 from Dow Corning for dip B. All Silquest silanes were obtained from GE silicones. We found no difference in performance between these different sources of acryloxy organosilane.

The epoxy silane used for Dip B was Silquest A187 and for Dip C was Q-1-6106 from Dow Corning.

The vinyl silane in Dip C was Z6300 from Dow Corning and the amino silane used for Dip D was Silquest Y-9669 from GE silicones.

5

#### SPAF (Strap Peel Adhesion Force) ASTM D 4393

The peel test is designed to measure the force required to separate two textile layers vulcanized between thick rubber layers with a thin intermediate rubber layer between these textile layers. To obtain the textile layers we used closely spaced parallel cords. Figure 2 shows a sample of a cord reinforced rubber article prior to pressing and vulcanization. For the SPAF test the top rubber layer 20 would be a thick layer and the lower layer 21 would be the thin layer beneath the top layer of cord fabric 22. There would then be a further layer of cords and a further layer of thick rubber beneath this. These are not shown in figure 2 because figure 2 is also representative of a composite article comprising silicone rubber reinforced with polyaramid cord.

15 For the test samples the intermediate silicone rubber layer between the cord layers was approximately 1 mm thick. After vulcanizing at a suitable elevated temperature and pressure for up to 15 minutes the test specimens were cut into 20 mm wide strips with a length of at least 70 mm and with the cord running along the length. The peel strength of the test specimen was determined using a recording tensile tester at a speed of 100 mm/min.

20 The adhesion is expressed as average peeling force plus or minus the standard deviation, omitting the initial force peak and measured between 20 and 70 mm strip-length.

#### Rubber coverage test

25 Rubber coverage is judged by three people examining the strips after testing according to the SPAF test described above. When the cords are totally covered by the coating or the rubber it is given a coverage score of 100%. A totally uncovered cord fabric is given a score of 0% and intermediate degrees of cover are judged against standards in increments of 20%. A value of 60% is considered to be an excellent coverage for most cord textile reinforced rubber products as this indicates that the bond fails by fracture of the rubber and not by parting at the rubber and reinforcement interface. However, lower values can be useful provided the overall bond strength is nearly as high as the internal strength of the rubber.

30

Table 2


		Unactivated polyaramid	Epoxy activated polyaramid	Plasma activated polyaramid	Epoxy and plasma activated polyaramid
Dip A	SPAF (N/cm <sup>2</sup> )	65.6 ± 20.4	82.2 ± 7.8	-	-
	Rubber coverage %	15%	60%	-	-
Dip B	SPAF (N/cm <sup>2</sup> )	74.5 ± 13.7	78.7 ± 6.6	86.9 ± 5.6	87.7 ± 4.2
	Rubber coverage %	40%	40%	60%	60%
Dip C	SPAF (N/cm <sup>2</sup> )	54.9 ± 14.3	67.0 ± 5.1	61.5 ± 3.7	68.5 ± 2.7
	Rubber coverage %	15%	20%	15%	20%
Dip D	SPAF (N/cm <sup>2</sup> )	50.2 ± 18.6	59.0 ± 14.9	39.7 ± 9.4 <sup>a</sup>	75.8 ± 13.6 <sup>a</sup>
	Rubber coverage %	2%	5%	2% <sup>a</sup>	20% <sup>a</sup>

<sup>a</sup> means that the plasma activation was by means of a plasma of air into which was injected an aerosol of water/glycol in a nitrogen carrier, otherwise plasma activation was by air plasma at a pressure of about 6 bar.


### Claims

1. A composite article comprising a silicone rubber matrix reinforced with polyaramid textile characterized in that the polyaramid textile is bonded to the silicone rubber by means of a bonding composition comprising an acryloxy organosilane.
2. A composite article according to claim 1 in which the polyaramid is activated with an epoxy compound.
3. A composite article according to any preceding claim in which the polyaramid is a p-phenylene polyaramid.
4. A composite article according to any preceding claim in which the bonding composition further comprises an epoxy organosilane.
5. A composite article according to claim 4 in which the bonding composition further comprises a vinyl organosilane.
6. A composite article according to any preceding claim in which the organosilane is a trimethoxy silane.
7. A composite article according to any preceding claim in which the polyaramid textile comprises polyaramid single end or cabled cords.
8. A composite article according to any one of claims 1 to 6 in which the polyaramid textile is a fabric; particularly a weft insertion warp knit fabric having polyaramid weft and/or warp yarns.
9. A process for manufacturing an polyaramid reinforced silicone rubber article comprising the steps of:
  - a) Selecting a polyaramid textile,
  - b) Optionally activating the polyaramid textile with an epoxy compound, and/or optionally activating the polyaramid textile with a plasma,
  - c) Dipping the polyaramid textile into an organosilane dip comprising acryloxy organosilane, and
  - d) Bonding the dipped polyaramid textile to silicone rubber.
10. A process according to claim 7 wherein the organosilane dip further comprises an epoxy organosilane.


11. A process according to claim 7 or claim 8 wherein the organosilane dip is an aqueous dip.
12. A process according to claim 7 in which epoxy activation is followed by plasma activation, which is, in turn, followed by the organosilane dipping step.
13. A process according to claim 10 in which the plasma activation comprises an air plasma.
14. A process according to claim 11 in which the plasma activation comprises an air plasma further including water as an aerosol.
15. A process according to claim 12 in which the organosilane dip further comprises an amino functional organosilane.



1/1



**Fig 1**



**Fig 2**